

The Contractor shall distribute to each residence or business along a road to be paved, a flyer with notification of the work to be done and the dates it will be performed. Also to be included is a request that all vehicles be removed from the street during this time period. The flyers are to be delivered 2 to 4 days prior to the actual start date of the construction.

MEASUREMENT AND PAYMENT

Price adjustments for asphalt binder for plant mix will be made in accordance with Section 620 of the January 2018 Standard Specifications for Roads and Structures.

The base price index for asphalt cement for plant mix is \$492.86 per ton.

This base price index represents an average F.O.B. selling prices of asphalt cement at supplier's terminals on April 1 2020.

Pay Item	Pay Unit
Asphalt Binder for Plant Mix, Grade PG 64-22	Ton
Asphalt Concrete Surface S9.5B	Ton

PLACEMENT LIMITATIONS

Asphalt mixtures that have temperatures of less than 225°F, when ready to dump into the mechanical spreader, will be rejected. All compaction rolling shall be completed prior to the mat cooling down to 175°F. Finish rolling may be performed at a lower mat temperature. Use steel roller for initial compaction on mat then finish compaction on mat with a pneumatic rubber tire roller. Contractor shall not use vibration on the rollers.

PAVEMENT TOLERANCE

The surface will be tested by using a 10-foot straightedge. The variation of the surface from the testing edge of the straightedge between any two contacts with the surface shall not be more than 1/4 inch. Humps and depressions exceeding the specified tolerance shall be corrected, or the defective work shall be removed and replaced with new material.